

Technical Data Sheet

Asbestos S	
Description:	 Asbestos Sealer is an acrylic based, saturation/penetration coating suitable for both porous and non-porous asbestos, cement sheet and masonry surfaces where stabilisation and weather proofing is required. Asbestos Sealer ensures a superior binding properties in order to stabilise the surface whilst improving adhesion of the range of Nutech roof coating systems including; NuFlex, TileFlex or NXT Cool Zone.
Features:	
	 Excellent stabilising and adhesion properties to weathered and porous asbestos Suitable for cement sheet or masonry surfaces Excellent chemical resistance Weatherproofing performance High resistance to mould and fungus
Safety	Observe all Occupation Health and Safety (OH&S) precautions.
Precautions:	Refer to the relevant Safety Data Sheets (SDS) for product safety related information. For further information and support: Nutech Paint 03 9770 3000 <u>https://nutechpaint.com.au/</u>
accordance w asbestos base	Any preparation processes to be used in the treatment and disposal of asbestos must be done so in ith controlled regulatory guidelines and conducted by TRAINED PROFESSIONALS experienced in handling d materials. Ination can be found at: https://www.safeworkaustralia.gov.au/asbestos
Provisions:	Determining whether a roofing or sheeting system is cement or asbestos based is difficult to identify.
Provisions.	Correct identification is critical in taking all necessary precautions in dealing with this substrate.
	There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/
	There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/
	There are specialised companies who offer testing kits to assist in identification:
	There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action.
	 There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action. Only apply between 10°C and 30°C ambient air temperatures Application in extreme hot or cold temperatures is not recommended
Chemical Type:	 There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action. Only apply between 10°C and 30°C ambient air temperatures Application in extreme hot or cold temperatures is not recommended In cold weather do not topcoat until the first coat is fully dried
	 There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action. Only apply between 10°C and 30°C ambient air temperatures Application in extreme hot or cold temperatures is not recommended
Chemical Type: Product Attributes:	There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action. • Only apply between 10°C and 30°C ambient air temperatures • Application in extreme hot or cold temperatures is not recommended • In cold weather do not topcoat until the first coat is fully dried Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0
Product	There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action. • Only apply between 10°C and 30°C ambient air temperatures • Application in extreme hot or cold temperatures is not recommended • In cold weather do not topcoat until the first coat is fully dried Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water
Product	There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action. • Only apply between 10°C and 30°C ambient air temperatures • Application in extreme hot or cold temperatures is not recommended • In cold weather do not topcoat until the first coat is fully dried Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C
Product Attributes:	There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action. • Only apply between 10°C and 30°C ambient air temperatures • Application in extreme hot or cold temperatures is not recommended • In cold weather do not topcoat until the first coat is fully dried Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C Minimum Film Thickness (dry): 20 – 25µm
Product Attributes: Typical	 There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action. Only apply between 10°C and 30°C ambient air temperatures Application in extreme hot or cold temperatures is not recommended In cold weather do not topcoat until the first coat is fully dried Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C Minimum Film Thickness (dry): 20 – 25µm Typical projects include:
Product Attributes:	 There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action. Only apply between 10°C and 30°C ambient air temperatures Application in extreme hot or cold temperatures is not recommended In cold weather do not topcoat until the first coat is fully dried Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C Minimum Film Thickness (dry): 20 – 25µm Typical projects include:
Product Attributes: Typical Applications:	There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action. • Only apply between 10°C and 30°C ambient air temperatures • Application in extreme hot or cold temperatures is not recommended • In cold weather do not topcoat until the first coat is fully dried Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C Minimum Film Thickness (dry): 20 – 25µm Typical projects include: Domestic & Multi Density Residential, Industrial and Commercial uses for priming and binding asbestos
Product Attributes: Typical	There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action. • Only apply between 10°C and 30°C ambient air temperatures • Application in extreme hot or cold temperatures is not recommended • In cold weather do not topcoat until the first coat is fully dried Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C Minimum Film Thickness (dry): 20 – 25μm Typical projects include: Domestic & Multi Density Residential, Industrial and Commercial uses for priming and binding asbestos and cement sheet.
Product Attributes: Typical Applications: Appearance: Coverage /	There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action. • Only apply between 10°C and 30°C ambient air temperatures • Application in extreme hot or cold temperatures is not recommended • In cold weather do not topcoat until the first coat is fully dried Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C Minimum Film Thickness (dry): 20 – 25μm Typical projects include: Domestic & Multi Density Residential, Industrial and Commercial uses for priming and binding asbestos and cement sheet. Opaque white or off-white viscous liquid
Product Attributes: Typical Applications: Appearance:	There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action. • Only apply between 10°C and 30°C ambient air temperatures • Application in extreme hot or cold temperatures is not recommended • In cold weather do not topcoat until the first coat is fully dried Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C Minimum Film Thickness (dry): 20 – 25µm Typical projects include: Domestic & Multi Density Residential, Industrial and Commercial uses for priming and binding asbestos and cement sheet. Opaque white or off-white viscous liquid
Product Attributes: Typical Applications: Appearance: Coverage / Spread Rate:	There are specialised companies who offer testing kits to assist in identification: https://www.asbestosassessments.com.au/order-kit/asbestos-test-kit/ For specific repairs to asbestos surfaces, PROFESSIONAL ADVICE AND SUPPORT MUST BE SOUGHT to determine the safest course of action. • Only apply between 10°C and 30°C ambient air temperatures • Application in extreme hot or cold temperatures is not recommended • In cold weather do not topcoat until the first coat is fully dried Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C Minimum Film Thickness (dry): 20 – 25µm Typical projects include: Domestic & Multi Density Residential, Industrial and Commercial uses for priming and binding asbestos and cement sheet. Opaque white or off-white viscous liquid 4m²/L per coat – depending on surface porosity Note: Application to saturation point is recommended to ensure suitable surface binding properties



Recommended	Asbestos, cement sheeting and masonry surfaces where water proofing is necessary
Substrates: Mixing/	Stir thoroughly prior to use.
Thinning:	
Test Patch:	Maximum dilution: 10%. Conduct a small test patch to ensure adequate product performance and adhesion.
Substrate note:	Clean the substrate as best as possible without disturbing the surface.
Application:	Very low pressure airless spray
	Brush or roller
Preparation:	HIGH PRESSURE WATER CLEANING OF ASBESTOS IS PROHIBITIED UNDER STATE AND FEDERAL LAW. ALL PREPARATION AND RINSING MUST BE PERFORMED UNDER VERY LOW RINSE WATER PRESSURE
	Moss, Mould & Lichen
	 For affected areas, saturate the surface in accordance with the relevant TDS with undiluted Nutech Hypo at approximately 1 litre per 5m2 using a pump sprayer or watering can. Allow a minimum 24 hours for Hypo to activate
	 Gently rinse the surface with very low water pressure only
	After treatment, allow the roof surface to thoroughly dry \overline{p} rior to coating
Application:	Application by brush or roller to saturation point, observing the recommended spread rate outlined in this
	TDS.
	Application in cooler weather is recommended to ensure maximum penetration of Asbestos Sealer.
Drying Time:	Ambient conditions @ 25°C and 60% relative humidity.
Touch Dry:	30 Minutes
Recoat:	2 hours
Full Cure:	24 Hours
Clean Up:	Protecting Our Environment is important to Nutech Paints:
	Clean up hands and equipment with fresh warm water or dispose of equipment. Do not pour left over paint down drains or in rubbish bins. Unwanted paint should be kept in a sealed container and then disposed of via special waste collection services.
	Empty paint containers should be left open in a well ventilated area to dry out. Dispose of empty paint containers in accordance with local authority guidelines. Always check with your local council first.
First Aid:	SEEK IMMEDIATE MEDICAL ATTENTION. Refer to the appropriate Nutech Safety Data Sheet (SDS) for
	further information.
	For medical emergencies only, call: 000
	 In case of eye contact, flush thoroughly with water for at least 15 minutes
	 In case of skin contact, wash affected areas with soap and water
	Remove and wash contaminated clothing
	If inhalation causes physical discomfort, remove to fresh air
	If discomfort persists, any breathing difficulty occurs or if swallowed, seek medical advice



Nutech Paint warrants its products to be free from defects in material and workmanship. Nutech's sole obligation and Buyer's exclusive
remedy in connection with the products shall be limited, at Nutech's option, to either replacement of products not conforming to this
Warranty or credit to Buyer's account in the invoiced amount of the non-conforming products. Any claim under this Warranty must be made
by Buyer to Nutech Paint in writing within five days (5) of Buyer's discovery of the claimed defect, but in no event later than the expiration of
the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify Nutech Paint of such non-
conformance as required herein shall bar Buyer from recovery under this Warranty. Nutech Paint makes no other warranties concerning the
product. No other warranties, whether express, implied or statutory, such as warranties of merchantability or fitness for a particular purpose,
shall apply. In no event shall Nutech Paint be liable for consequential or incidental damages.
Our goods come with guarantees that cannot be excluded under Australian Consumer Law. You are entitled to a replacement or refund for a
major failure and for compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure.
Nutech's liability on any claim of any kind, including claims based upon Nutech's negligence or strict liability, for any loss or damage arising ou
of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which gives rise to the claim. In no event shall Nutech be liable for consequential or incidental damages.
The information provided in this data sheet is based on many years' experience and is correct to the best of our knowledge. However, since
the use of our product, surface conditions, weather and a number of other factors are completely beyond our control, we can only be responsible for the quality of our product at the time of dispatch. For more information please contact Nutech Paint. As this information is of a general nature, we cannot assume any responsibility in individual cases.
The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous
product development.
-

response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by buyers having requisite skill and know-how in the industry and therefore it is for buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that buyer has done so, at its sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

NuTech Paint Pty Ltd T +61 3 9770 3000 4 Keppler Circuit Seaford VIC 3198 nutech.com.au

